

MICRONIZED COMPOUND NON-ALTERABLE



- GENERAL SHEETS -

MICROVAL COMPOUND RECOMMENDED ACCORDING TO THE HARDNESS OF THE METAL TO BE TREATED

	° HB	° HRB	° HRC	° HV	
					
	347	110	37	357	
	357	111	38	371	
	367	111	39	381	
	377	112	40	391	
	387	112	41	404	
MICROVAL giallo	398	113	42	416	grigio MICROVAL
mixture of oxides and carbides	408	114	43	427	mixture of oxides and carbides
	419	114	44	440	
	430	115	45	453	
	442	115	46	468	
	453	116	47	482	
	464	117	48	497	
	476	117	49	513	
	488	118	50	528	
MICROVAL grigio	500	118	51	549	grigio MICROVAL
mixture of oxides and carbides	512	119	52	567	mixture of oxides and carbides
	524	119	53	585	
	536	120	54	604	
	548	120	55	623	
	561	120	56	646	
	574	121	57	666	
	587	121	58	693	
	600	122	59	720	
	613	122	60	746	
MICROVAL rosso	627	122	61	772	verde MICROVAL
standard cut monocrystalline diamond	635	123	62	797	monocrystalline diamond with more uniform cut
	650	123	63	826	
					

MICROVAL **blu** Polycrystalline diamond



RODITOR & PHILADELPHIA

DISCHI E PASTE PER IL TRATTAMENTO DELLE SUPERFICI
BUFFS AND COMPOUNDS FOR SURFACE TREATMENT

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001 • ISO 14001
ISO 45001

STANDARD GRITS	
MICRONS	F.E.P.A.
1	1.500
3	1.200
5	1.000
7	800
9	600
15	500/400
25	360
30	320
45	240
60	180

° **HB** = BRINELL

° **HRB** = ROCKWELL "B"

° **HRC** = ROCKWELL "C"

° **HV** = VICKERS

The information contained in this sheet represents the best of our current knowledge on the subject, without however providing guarantees on their validity.
The user is therefore responsible for further investigation, by means of this information.

01/01/25

RODITOR & PHILADELPHIA SRL Via San Donnino, 13 - 25028 VEROLANUOVA (BS) - ITALY

Tel.+39-030-931211- Fax+39-030-931768 www.roditor.it infoitalia@roditor.it info@roditor.it PEC: roditorphiladelphiasrl@pec.it SDI T04ZHR3

P.IVA IT 00552840985 - C.F. 00301370177 - EXPORT M BS007184 - REG.IMPR. BS 00301370177 - REA BS179373 CAP. SOC. € 51.480,00